

杰星橡胶磁体的磁特性及物理性能

种类	参数	同性	半异性	异性
胶片	Br(Gs)	≥ 1800	≥ 2000	≥ 2400
	Hcb (Oe)	≥ 1400	≥ 1500	≥ 2000
	Hcj(Oe)	≥ 2100	≥ 1900	≥ 2500
	(BH)Max(MGoe)	≥ 0.68	≥ 0.88	≥ 1.3

JS-Q608-A-1203

Magnetic Properties&Physical Characteristics of Rubber Magnet,HJ

Type	Material	Isotropic	Semi-anisotropic	Anisotropic
Rubber Magnet	Br(Gs)	≥ 1800	≥ 2000	≥ 2400
	Hcb (Oe)	≥ 1400	≥ 1500	≥ 2000
	Hcj(Oe)	≥ 2100	≥ 1900	≥ 2500
	(BH)Max(MGoe)	≥ 0.68	≥ 0.88	≥ 1.3

JS-Q608-A-1203